
Product data Laminate flooring Classic

LC 55



Tests	DIN/EN	Laminata flooring Classic LC EE
	standard	Laminate flooring Classic LC 55
product composition		
Type of covering:		Flooring panel with top layer made from specially-resined decor paper
Total thickness:		approx. 7mm
Effective measurement: (length × width)		1288 x 198mm
Product structure:		a. Overlay b. Decorative paper c. HDF base board (approx. 890 kg/m 3 \pm 3%) d. Backing
· · · · · · · · · · · · · · · · · · ·		Multiclic
Wear class:	EN 13 329	23 31
Wear resistance:	EN 13 329 (appendix E)	AC3 (= IP ≥ 2,000 U)
Impact resistance:	EN 13 329 (appendix F)	IC 1
Stain resistance:	EN 13 329 (EN 438-2/26)	Group 1: grade 5 Group 2: grade 5 Group 3: grade 4-5
Colour fastness:	EN 13 329 (EN ISO 105)	≥ stage 6 on the blue wool scale
Fire behaviour:	EN 13 501	C _{fl} -s1 (hardly flammable)
Slip resistance:	EN 14 041 / 13 893	DS
Scratch resistance:	EN 438-2/25	≥ 5 N
Formaldehyde emissions (E1 = 0.1 ppm):	EN 717-1	≤ 0.05 ppm
Indent after constant load:	EN 13 329 (EN 433)	no visible changes
	Total thickness: Effective measurement: (length × width) Product structure: Locking method: Wear class: Wear resistance: Impact resistance: Stain resistance: Colour fastness: Fire behaviour: Slip resistance: Scratch resistance: Formaldehyde emissions (E1 = 0.1 ppm):	Total thickness: Effective measurement: (length × width) Product structure: Locking method: Wear class: EN 13 329 (appendix E) Impact resistance: EN 13 329 (appendix F) Stain resistance: EN 13 329 (EN 438-2/26) Colour fastness: EN 13 329 (EN 438-2/26) Colour fastness: EN 13 329 (EN 150 105) Fire behaviour: EN 13 501 Slip resistance: EN 14 041 / 13 893 Scratch resistance: EN 438-2/25 Formaldehyde emissions (E1 = 0.1 ppm): Indent after constant load: EN 13 329

08|17

	Castor resistance:	EN 13 329 (EN 425)	no visible changes or damage with soft, standard castors
	Behaviour on simulation of shifting furniture foot:	EN 13 329 (EN 424)	no visible damage
	Underfloor heating:		Suitable for hot-water underfloor heating Electrical underfloor heating is generally suitable when it is built into the floor screed or the concrete layer and thus does not lie on the concrete layer as foil heating. The heating elements pipes wires must lie across the entire area and not just be partly present. If the area is only partially heated, the floor covering must have expansion joints (system profile strips). The maximum permitted surface temperature is 29°C. Standard foil heating systems are generally not recommended. One exception is self-regulating heating systems which maintain the 29°C surface temperature.
	Heat transfer resistance:	EN 12 667	with MEISTER-Twin Control: 0.104 m ² K/W
olerances			
	Right-angle of the elements:	EN 13 329	target values met
	Determination of edge straightness:	EN 13 329	target values met
	Surface flushness:	EN 13 329	target values met
	Joint opening between the elements:	EN 13 329	target values met
Seneral dat	a on environment, installation and c	are	
	Blue Angel:	RAL-UZ 176	awarded
	Disposal:		Residual pieces can be disposed of in household refuse (e.g. thermal treatment) Dispose large quantities according to municipal provisions (e.g. recycling centres) An energetic utilization in authorized plants is recommended.
	Cleaning and care:		Cleaning after construction work/ day-to-day cleaning: CC Laminate Cleaner Special cleaning: CC-Elatex Stain Remover
	Areas of application:		The Classic flooring LC 55 is suitable for all dry living areas as well as for commercial areas with medium wear, e. g. hotel rooms, small offices, conference rooms etc. This flooring is not suitable for installing in humid rooms (bathrooms, saunas etc.). Special requirements apply to treatmen rooms and medical practices.
	Preconditions for installation:	DIN 18 365	The substrates must be ready for laying on according to the generally recognised rules of the trade, taking into account VOB (German construction contract procedures), part C DIN 18 365 "parquetry work". The substrate must be dry (in the case of mineral substrates max. 2% or with underfloor heating 1.8 %, with anhydrite screed max. 0.5% or with underfloor heating 0.3 % residual moisture – measured with CM devices) even, firm and clean. Additionally, any unevenness of 3mm/ per initial metre and 2mm per further metre must be evened out according to DIN 18 202, table 3, line 4.The installation instructions provided with the product must be observed.













MeisterWerke Schulte GmbH reserves the right to make alterations to material and structures when this serves to improve the quality.

08|17